










LABOND “ISOFOR L001” Light Weight Concrete System – L001F Foaming Concrete Model

立康牌 L001 輕石屎系統 - L001F 泡沫型號

<p>Step 1 步驟 1</p>	<p>Step 2 步驟 2</p>	<p>Step 3 步驟 3</p>
<p>Client require raised-up flooring by light weight concrete with density not greater than 700kg/M³ 客戶要求用輕石屎將地台升高，其密度不可超過 700 kg/M³</p>	<p>Site Examination to clear up water sitting area and prepare necessary shuttering 檢查及清除現場積水，加設封閉等工序。</p>	<p>Master Proofer’s technical representative is observing if equipments and materials are properly setting up 萬寶行技術顧問代表正觀察安裝器具及物料準備。</p>
 <p align="center">1</p>	 <p align="center">2</p>	 <p align="center">3</p>
<p>Step 4 步驟 4</p>	<p>Step 5 步驟 5</p>	<p>Step 6 步驟 6</p>
<p>Start mixing according to formulation and in order as water, Isofor agent (wait until foaming up), then finally cement. 開始混合工序，依照預設配方將水，輕石屎水(混合直至出現很多泡沫)及水泥順序放入。</p>	<p>Mixing all component until homogenous mortar is formed. (Normally not longer than 1 minute) 大概一分鐘內便將混合成一均衡輕石屎泥漿。</p>	<p>Start pouring mortar into site, it has high liquidity and will run automatically to level. 將輕石屎漿傾倒在施工位置。高水力流動性的石屎泥漿會自動流平。</p>
 <p align="center">4</p>	 <p align="center">5</p>	 <p align="center">6</p>
<p>Step 7 步驟 7</p>	<p>Step 8 步驟 8</p>	<p>Step 9 步驟 9</p>
<p>Excessive air trapping inside the mortar is releasing and broken over the surface and then resurfacing automatically. 在輕石屎漿體內多餘的汽泡會自動悉出及後自動流平狀。</p>	<p>A professional worker is examining there are any “bleeding” of mortar due to improper water-cement-agent ratio. He will dispose that part of “bleeding” mortar if it is found. 一名專業工人正在檢查漿體是否有“出水”現象。一般是於錯誤“水-英泥-輕石屎劑”比例引至。如有此情形，工人會將“出水”部份清除。</p>	<p>Leave the site not be disturbed and make sure not in touch with new water source, like raining etc. New flooring will be ready for light traffic after 24 hours. 完成施工後，漿體必須受保護，不能接觸新水份，如下大雨等。輕石屎層會在 24 小時後初部完成凝固及可作輕度踐踏。</p>
 <p align="center">7</p>	 <p align="center">8</p>	 <p align="center">9</p>