



Flexfixer P933

High Performance Penetrating Primer

高效能三合土底油

1.0 Description

Flexfixer P933 is an acrylic resin-based setting and specifying penetration primer in solution.

- Excellent for the preparation of surfaces regardless of the type of final top coating to be applied.

2.0 Typical Application

- Improves the cohesion of porous and heterogeneous surfaces.
- Sets chalky surfaces.
- Is permeable to water vapor and allows the surface to breathe.
- Is not sensitive to the surface alkalinity and is therefore perfectly adapted to recoat old silicates paints.
- Can be applied in cold and humid weather provided that the substrates are not frozen.
- Adheres perfectly on almost all old sound substrates.

3.0 Area of application

Outdoors and indoors on every old or new masonry.

4.0 Characteristics

Composition	Binder:	Acrylic resins.
	Pigment:	Titanium oxide and material extenders.
	Solvent:	Mixture of spirits.
Visual appearance in recipient:	Slightly thixotropic, ready-to-use.	
Density:	1.40 +/- 5.05.	
Drying at 20 °C and 65% of relative humidity: Dry in 2 hours.		
Suitable for addition coat:	24 hours.	
Visual appearance of film:	Matt.	
Flash point:	35°C	
Keeps:	One year in original and unopened drum. Keep away from heat.	
Hygiene and safety:	Inflammable. Use inside only in well ventilated rooms.	
VOC Content:	125 g/L	



Flexfixer P933

High Performance Penetrating Primer



5.0 Application Instructions

Application must be in accordance with Unified Technical Documentation (D.T.U.) 59/1 and 59/2.

Surface preparation:

- **New surfaces:** Vigorous brushing followed by dust removal.

- **Old surfaces:**
 - * Slightly powdery or chalky: vigorous brushing following by dust removal.
 - * Chalky or very chalky: sandpaper, vigorous brushing, dust removal.
 - * Old paintworks: Remove all non-well adhering flaking parts by mechanical abrasion, descaling, or better water jet washing, followed by a thorough drying.

Application equipment: Brush, sheepskin roller or airless spraygun.

Dilution: For application with airless gun, dilute with 15 % of white spirit 17 or naphta solvent.
For application using brush or roller, dilute from 0 to 10 % with white spirit 17.

Equipment Cleaning: With white spirit 17 or naphta solvent.

6.0 Covering capacity

5 to 6 m² per kg and per coat according to the substrate and the application equipment.

7.0 Packaging

25 kg drum