



# Ralliprime R160

## Primer for Polyurethane Coating / Concrete Surface

### 1.0 Description

LABOND Primer R160 is a one component type primer cured by chemical reaction with moisture from the air, which offer excellent operation condition, dryness and good adhesion for polyurethane coat and cement base surface. It also provides certain degree of water resistance to the surface.

### 2.0 Technical Data

Appearance	Brownish liquid
Non volatile (%)	38 ± 1
Viscosity (at 25°C, cps)	Max. 100
Drying time (min)	60

### 3.0 Application Guide

- Apply by brush without dilution directly onto concrete, P.C panel and allow 3 to 4 hours for completely cured.
- General coverage of 0.2 – 0.3 kg/m<sup>2</sup>.

### 4.0 Health and Safety

- Be careful of absorption and fire since contains a solvent.
- Seal up in stock since it will react with moisture in air.
- When it is put on clothes and skin, wash with soap water

### 5.0 Technical Service

The Technical office of MASTER PROOFER COMPANY LTD are available for advice on any of LABOND's products.

### 6.0 Packaging

1 Liter / Can 5 Liters / Can

LABOND