



香 港 標 準 及 檢 定 中 心
Hong Kong Standards and Testing Centre

Date : 2004-05-14
No. : HC151169

TEST REPORT

Page 1 of 2

- Applicant(Code:MAP007)** : Master Proofer Co Ltd
Unit I 8/F On Ho Ind Bldg
17-19 Shing Wan Rd
Tai Wai NT
- Description of Samples** : One submitted sample said to be Labond MPSeal-I301pu
Flexible low viscosity polyurethane injection resin.
Reference No.: I301pu
Country of Origin: HK
- Date Samples Received** : 2004-05-03
- Date Tested** : 2004-05-12 to 2004-05-13
- Investigation Requested** : BS 6920: Part 1: 1996: Clause 8: The extraction of metals
Suitability of non-metallic products for use in contact with water
intended for human consumption with regard to their effect on the
quality of the water
- Conclusions** : The test results of the submitted sample **complied** with the
specifications of BS 6920: Part 1: 1996: Clause 8: The extraction of
metals.


Anne Chuah, CFD
For Chief Executive



This report shall not be reproduced unless with prior written approval from the Hong Kong Standards and Testing Centre.



香港標準及檢定中心
Hong Kong Standards and Testing Centre

Date : 2004-05-14
No. : HC151169

TEST REPORT

Page 2 of 2

Method(s) Used:

BS 6920: Part 1: 1996 and BS 6920: Section 2.6: 1996

Test Results:

Test Item(s)	Results ($\mu\text{g/L}$)	Max. allowable concentration# ($\mu\text{g/L}$)
1. Aluminium	<100	200
2. Antimony	<10	10
3. Arsenic	<10	50
4. Barium	<100	1000
5. Cadmium	<5	5
6. Chromium	<10	50
7. Iron	<100	200
8. Lead	<10	50
9. Manganese	<10	50
10. Mercury	<1	1
11. Nickel	<10	50
12. Selenium	<10	10
13. Silver	<10	10

Notes: # quoted from Table 1 of BS 6920: Part 1: 1996
< denotes less than
 $\mu\text{g/L}$ denotes microgram per Litre

***** End of Test Report *****